

Automotive Flammability of Interior Materials (FMVSS 302)

49 CFR 571.302

Customer Information
Chemicar USA 670 New York Street Memphis, TN 38104

Sample Information
Total Coat: HD Bed Liner / Tekton 64 Floor Coating

Sample	Burn Distance (mm)	Total Time (sec)	Burn Rate (mm/min)
1	0	0.0	0.0
2	0	0.0	0.0
3	0	0.0	0.0
4	0	0.0	0.0
5	0	0.0	0.0

Acceptance Criteria:
The burn rate must not exceed 102 millimeters per minute on any sample.

Result
<input checked="" type="checkbox"/> PASS <input type="checkbox"/> FAIL

Notes:
Flame self-extinguished prior to crossing the 38 mm mark. Burn Rate recorded as zero.

RESULTS RELATE ONLY TO THE ITEMS AS RECEIVED AND TESTED. THIS REPORT SHALL NOT BE REPRODUCED, EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL.

Tested by: Gregory Thomas 27-Oct-21
 Lab Technician

Approval: *Andrew Feghali* 27-Oct-21
 Andrew Feghali, Lab Manager